

# Blackout Film

## OPTICAL & SOLAR PROPERTIES

|                                  | Single Pane |
|----------------------------------|-------------|
| Visible Light Transmitted        | 0 %         |
| Visible Light Reflected (Int)    |             |
| Visible Light Reflected (Ext)    | 6 %         |
| Ultra Violet Block               | 100 %       |
| Total Solar Energy Reflected     | 41 %        |
| Total Solar Energy Transmitted   | 0 %         |
| Total Solar Energy Absorbed      | 59 %        |
| Emissivity (Room Side)           | 0.72        |
| Glare Reduction                  | 100 %       |
| Shading Coefficient              | 0.20        |
| Solar Heat Gain Coeff. (G-Value) | 0.16        |
| U-Value Winter (IP)              | 0.98        |
| U-Value Winter (SI)              | 5.57        |
| Luminous Efficacy                | 0.00        |
| Total Solar Energy Rejected      | 84 %        |

R06930S - Blackout Film Pressure Sensitive Adhesive

Ed-D DS No 1800 February 2013