

# White Out Film

## OPTICAL & SOLAR PROPERTIES

|                                  | Single Pane | Double Pane |
|----------------------------------|-------------|-------------|
| Visible Light Transmitted        | 10 %        | 10 %        |
| Visible Light Reflected (Int)    |             |             |
| Visible Light Reflected (Ext)    | 48 %        | 50 %        |
| Ultra Violet Block               | 99 %        | 99 %        |
| Total Solar Energy Reflected     | 36 %        | 34 %        |
| Total Solar Energy Transmitted   | 17 %        | 15 %        |
| Total Solar Energy Absorbed      | 47 %        | 51 %        |
| Emissivity (Room Side)           | 0.90        | 0.90        |
| Glare Reduction                  | 89 %        | 89 %        |
| Shading Coefficient              | 0.37        | 0.49        |
| Solar Heat Gain Coeff. (G-Value) | 0.31        | 0.42        |
| U-Value Winter (IP)              | 1.07        | 0.49        |
| U-Value Winter (SI)              | 6.08        | 2.78        |
| Luminous Efficacy                | 0.27        | 0.19        |
| Total Solar Energy Rejected      | 69 %        | 58 %        |

R073WO - White Out Pressure Sensitive Adhesive Film

ED-A DS No 1801 February 2013